

SPYDER FAST GRIP: CLEAR



TYPICAL CHARACTERISTICS

Chemical base	Polyurethane
Colour	Transparent
Curing mechanism	Moisture
Density	1.13 ± 0.03 g/cm³
Skin formation time	5-10 minutes
Pressing time	15-20 minutes
Application temp	+5-+35°C
Temp resistance	-30 - +80°C
Standard	Conforms to D4 according DIN EN 204
Packaging	310ml tube
Manufacturing standard	ISO 9001:2015



DESCRIPTION

SPYDER FAST GRIP is a single component, fast curing polyurethane-based adhesive. It combines high bond strength with fast curing. It is used to bond almost all common building materials. The water resistance property makes it very good at bonding wooden surfaces where water can be an issue. It is fast curing, non shrinking, thixotropic, and is usable in slightly wet conditions. It has good filling properties, and has good weathering resistance.

RECOMMENDED USE

Suitable for the use in construction and repair applications where a permanent bond is required between porous/porous and porous/non-porous surfaces. Bonding wooden surfaces on areas where there is a constant moisture and water contact risk. It can be used for bonding to various kinds of construction materials such as wood, MDF, concrete, metal, polystyrene, Pu foam, marble, etc...

METHOD

- Can be applied with manual or pneumatic gun.
- The substrate must be dry and clean, free of dust and grease.
- Moistening the substrates slightly improves the adhesion.
- Do not apply the product at temperature below +5°C.
- **SPYDER FAST GRIP** should only be applied on one side.
- Mechanical fasteners must be used to keep the material together at least between 15-20min, while adhesive is curing completely.

IMPORTANT

Always read the Safety Data Sheet before use.

STORAGE

Store in a cool dry well ventilated area at between 5-25°C.

SHELF LIFE

12 months if stored between from the date of manufacture.

CLEANING

Tools can be cleaned with SOLVENT CLEANER whilst SPYDER FASTGRIP is still wet and mechanically once dry.

DISCLAIMER The Information provided herein, especially recommendations for the usage and the application of this products, is provided in good faith, & no liability on the part of AFT Aerosols Ltd is stated or implied. No employee of AFT Aerosols Ltd has the authority to waive or alter in any way the content of this document. Due to different materials used, as well as to varying working conditions, production techniques, & the requirements of the end users, all of which are beyond our control, we strongly recommend that thorough & extensive trials are carried out in order to test the suitability of our products with regard to the required processes and applications. This should also include an ageing test which should be applied to all substrates used. It is also the responsibility of the purchaser & end user of this product to ensure that all appropriate actions necessary for the protection of the environment, & for the health & safety of their employees are observed. This datasheet replaces all former versions.